


# SITEDRAIN™ SHEET 186-W

## PREFABRICATED SHEET DRAIN



### PRODUCT OVERVIEW

SITEDRAIN Sheet 186-W geocomposite drain is composed of a dimpled polymeric core with a woven monofilament geotextile bonded to the dimple side. The geotextile allows water to pass through while retaining backfill materials. The solid core allows water collection from one side and provides a continuous flow path to designated drainage exits.

SITEDRAIN Sheet 186-W is an economical solution for single-sided subsurface drainage applications requiring high strength, high flow capacity, and the performance properties of a woven monofilament geotextile.

PROPERTY <sup>1</sup>	TEST METHOD	UNIT OF MEASURE	Typical Value	MARV
<b>GEOTEXTILE</b>				
Material <sup>2</sup>			PP, WM	PP, WM
Survivability	AASHTO M288	Class	-	-
Grab Tensile Strength	ASTM D4632	lbs	430 x 240	365 x 200
		N	1,914 x 1,068	1,624 x 890
Grab Elongation	ASTM D4632	%	30 x 15	24 x 10
CBR Puncture	ASTM D6241	lbs	800	675
		N	3,560	3,004
Trapezoidal Tear	ASTM D4533	lbs	180 x 130	115 x 75
		N	801 x 579	512 x 334
UV Resistance	ASTM D4355	% / 500 Hrs	90	90
Apparent Opening Size (AOS) <sup>3</sup>	ASTM D4751	sieve	50	40
		mm	0.300	0.425
Permittivity	ASTM D4491	sec <sup>-1</sup>	2.7	2.1
Water Flow Rate	ASTM D4491	gpm / ft <sup>2</sup>	195	145
		Lpm / m <sup>2</sup>	7,944	5,907
<b>CORE</b>				
Compressive Strength	ASTM D6364 ASTM D1621	psf	18,000	-
		kPa	862	-
Thickness	ASTM D5199	in	0.4	-
		mm	10	-
In-Plane Flow Rate <sup>4</sup>	ASTM D4716	gpm/ft	21	-
		Lpm/m	261	-
<b>COMPOSITE</b>				
Available Roll Sizes	Dimensions (ft)	Weight (lbs)	AWD Item Code	
	4 x 50	48	10130	
	6 x 50	74	13020	

<sup>1</sup> Unless otherwise noted, all physical and performance properties listed are Typical Value or Minimum Average Roll Value (MARV) as defined in ASTM D4439.

<sup>2</sup> PP = Polypropylene; NPNW = Needle-Punched Nonwoven; WM = Woven Monofilament; SBNW = Spunbonded Nonwoven

<sup>3</sup> Values for AOS represent Maximum Average Roll Value (MaxARV).

<sup>4</sup> In-plane flow rate measured at 3,600 psf (172 kPa) compressive load and a hydraulic gradient of 1.0.

All technical information contained in this document is accurate as of publication. AWD reserves the right to make changes to products and literature without notice. Please refer to our website for the most current technical information available.